

IN THE CLAIMS:

Please enter the following amendments and/or additions:

AI Cont
1. (Currently Amended) A method for producing a light-emitting device comprising the steps of disposing a transparent electrode, one or more organic layers and a back side electrode on a substrate to provide a light-emitting structure, and disposing sealing parts on said light-emitting structure to isolate said one or more organic layers from external air, wherein said one or more organic layers comprises a light-emitting layer containing a phosphorescent compound, and said light-emitting layer, said back side electrode and said sealing parts are disposed in an inert gas atmosphere where both of a moisture concentration and an oxygen concentration are 100 ppm or less.

2. (Original) The method for producing a light-emitting device according to claim 1, wherein said one or more organic layers is isolated from external air after disposing said light-emitting layer until said sealing parts are disposed.

3. (Original) The method for producing a light-emitting device according to claim 1, wherein both of said moisture concentration and said oxygen concentration are 50 ppm or less.

4. (Original) The method for producing a light-emitting device according to claim 3, wherein both of said moisture concentration and said oxygen concentration are 30 ppm or less.

5. (Original) The method for producing a light-emitting device according to claim 1, wherein at least one of said organic layers is formed by a wet film-forming method.

6. (Original) The method for producing a light-emitting device according to claim 1, wherein said one or more organic layers comprises a hole-injecting layer in contact with said light-emitting layer and said hole-injecting layer over said transparent electrode.

7. (Original) The method for producing a light-emitting device according to claim 6, wherein both of said hole-injecting layer and said light-emitting layer are formed by a

wet film-forming method.

8. (Original) The method for producing a light-emitting device according to claim 6, wherein said one or more organic layers further comprises an electron-transporting layer between said light-emitting layer and said back side electrode.

9. (Original) The method for producing a light-emitting device according to claim 1, wherein a weight ratio of said phosphorescent compound in said light-emitting layer is 0.1 to 70 weight % based on the total weight of said light-emitting layer.

10. (Original) The method for producing a light-emitting device according to claim 1, wherein said phosphorescent compound is an *ortho*-metallation complex.

11. (Original) The method for producing a light-emitting device according to claim 1, wherein an ultraviolet-hardening resin is used in combination with said sealing parts to isolate said one or more organic layers from external air.

12. (Currently Amended) A light-emitting device obtained by a method comprising the steps of disposing a transparent electrode, one or more organic layers and a back side electrode on a substrate to provide a light-emitting structure, and disposing sealing parts on said light-emitting structure to isolate said one or more organic layers from external air, wherein said one or more organic layers comprises a light-emitting layer containing a phosphorescent compound, and said light-emitting layer, said back side electrode and said sealing parts are disposed in an inert gas atmosphere where both of a moisture concentration and an oxygen concentration are 100 ppm or less.

13. (Original) The light-emitting device according to claim 12, wherein said one or more organic layers is isolated from external air after disposing said light-emitting layer until said sealing parts are disposed.

14. (Original) The light-emitting device according to claim 12, wherein both of said moisture concentration and said oxygen concentration are 50 ppm or less.

15. (Original) The light-emitting device according to claim 14, wherein both of said moisture concentration and said oxygen concentration are 30 ppm or less.

16. (Original) The light-emitting device according to claim 12, wherein at least

AMENDMENT UNDER 37 C.F.R. § 1.111

U.S. Appln. No. 10/000,323

one of said organic layers is formed by a wet film-forming method.

17. (Original) The light-emitting device according to claim 12, wherein said one or more organic layers comprises a hole-injecting layer in contact with said light-emitting layer and said hole-injecting layer over said transparent electrode.

18. (Original) The light-emitting device according to claim 17, wherein both of said hole-injecting layer and said light-emitting layer are formed by a wet film-forming method.

19. (Original) The light-emitting device according to claim 17, wherein said one or more organic layers further comprises an electron-transporting layer between said light-emitting layer and said back side electrode.

20. (Original) The light-emitting device according to claim 12, wherein a weight ratio of said phosphorescent compound in said light-emitting layer is 0.1 to 70 weight % based on the total weight of said light-emitting layer.
